



# Tyfo® SW-1 Epoxy Underwater Epoxy

## **DESCRIPTION**

Tyfo® SW-1 is a two part, 100% solids epoxy formulation consisting of epoxy resins, hardeners and inert fillers specifically designed for underwater applications on steel, concrete and mansory surfaces. Tyfo® SW-1 is used in fiber wrap applications, with or without an aggregate, as a protective coating or repair mortar to protect against damage and erosion in splash zone areas.

### **USES**

Tyfo® SW-1 is formulated for use as the patching material, primer and adhesive in fiber wrap applications. Tyfo® SW-1 can also be used to coat or repair concrete and steel materials in underwater and splash zone applications providing protection against corrosion, erosion and deterioration from salt or fresh water.

#### **COLORS**

The standard color of Tyfo® SW-1 is gray. Special colors are available subject to minimum order quantities.

# **MIXING**

Tyfo® SW-1 should be mixed above water and then transported below water. Premix Part A (base) and Part B (hardener) individually. Then combine Part A and Part B in a clean container and mix thoroughly with a slow speed motor and "Jiffy" type mixer. Scrape the side of the container at least once during mixing.

### **MORTAR GROUT**

A mortar grout can be made by mixing clean, dry silica sand with an equal volume of Tyfo® SW-1.

# **PACKAGING**

Order in 4-gallon pre-measured units in 5-gallon containers.

# **MIX RATIO**

100.0 parts of component A to 74.0 parts of component B by volume. (100 parts of component A to 56.0 parts of component B by weight.)

# SHELF LIFE

Two years in original, unopened and properly stored containers.

### STORAGE CONDITIONS

Store epoxy at  $40^{\circ}$  to  $90^{\circ}$  F ( $4^{\circ}$  to  $32^{\circ}$  C). Avoid freezing. Store rolls flat, not on ends, at temperatures below  $100^{\circ}$  F ( $38^{\circ}$  C). Avoid moisture and water contamination.

# **CERTIFICATE OF COMPLIANCE**

- Will be supplied upon request, complete with state and federal packaging laws with copy of labels used.
- Material safety data sheets will be supplied upon request.
- Possesses 0% V.O.C. level.

# HOW TO USE THE TYFO® SW-1 EPOXY

# SURFACE PREPARATION

Surface must be structurally sound, clean, free of loose or deteriorated concrete or coatings, marine growth or any other material which would impair adhesion. Sand blasting or high pressure water blasting are preferred methods of surface preparation. Application of Tyfo® SW-1 should begin promptly after surface preparation to reduce possibility of surface contamination.

# **APPLICATION**

Apply Tyfo® SW-1 at water and surface temperatures of 40° F or higher. Mix the Tyfo® SW-1 above water and transport underwater after mixing. Prime the surface by scrubbing the surface with neat Tyfo® SW-1. Apply by pressing the Tyfo® SW-1, mixed with or without aggregate, onto the surface with gloved hand or trowel. Work the Tyfo® SW-1 firmly into the surface to displace water. Build up the material to the desired thickness. The mortar grout (1:1 by volume) should be used for deep patching and the repair should be made in lifts of no more than 1.0 inch at a time. Allow each lift to achieve initial set prior to applying the next lift. Please refer to the NSF Listing for the NSF-61 Listed Application.

### **COVERAGE**

Tyfo® SW-1 coverage rates are approximate and will vary with temperature, surface porosity and texture. Following is the approximate coverage on a smooth surface:

Tyfo® SW-1	sq. ft./ga	I. thickness
or mortar	50	30 mils (1/32")
	25.5	62 mils (1/16")
	12.8	125 mils (1/18")

One gallon of Tyfo® SW-1 mixed with one gallon of dry aggregate will yield approximately 1.6 gallons of mortar.

Typical Material Properties at 75° F.		
Mixing ratio, by wt.	100:56	
Specific Gravity	1.6	
Viscosity A & B mixed, cps	14,000 - 18,000	
Gel Time, 65° F, hours	2.5 - 3.5	
ASTM D695, 7 day compressive strength, psi	7,000 - 8,000	
ASTM D695, 7 day compressive strength, mortar, psi (gel/uw:sand – 1:1 by volume)	8,000 - 9,000	
ASTM D2240 Shore D hardness	80 - 85	

# **CAUTION!**

Do not thin or dilute Tyfo® SW-1. Do not mix or apply below 40°F. Use only clean, oven dry aggregate to produce mortar. Tyfo® SW-1 is not designed to resist hydrostatic pressure from the negative side. Agitation of the product once under water should be minimized. When applying in a splash zone, protection should be provided from wave action under the product has reached initial cure (8-10 hours). Due to the many variables which can exist in underwater applications, a test application under job site conditions is recommended prior to the start of every project to evaluate both application techniques and adhesion properties.

Packaging: 4 gallon pre-measured kits

Storage: 40-90°F

Shelf life: 2 years in protected storage

Freight Class: Class 60

#### **COMPONENT A - Irritant:**

Component A contains epoxy resin. Vapors can cause respiratory irritation. Contact may cause skin or eye irritation. Can cause sensitization after prolonged or repeated exposure. Use safety goggles and chemical resistant gloves. Use only with adequate ventilation.

#### **COMPONENT B - Irritant:**

Component B is corrosive and contains amines. Contact with skin may cause severe burns. Avoid eye contact. Product is a strong sensitizer. Use of safety goggles and chemical resistant gloves recommended. Remove contaminated clothing. Avoid breathing vapors. Use adequate ventilation. Use of an organic vapor respirator recommended.

#### **FIRST AID**

In case of skin contact, wash immediately and thoroughly with soap and water. For eye contact, flush immediately with water for 15 minutes and consult a physician. For respiratory problems, remove person immediately to fresh air.

### **CLEANUP**

Clean tools and application equipment immediately after use with xylene or a similar approved solvent. Clean spills and drips while wet with approved solvent. Collect with absorbent material. Dispose of in accordance with current local, state and federal regulations. Read material safety data sheet before using. Uncured material can be removed with approved solvent. Cured materials can only be removed mechanically.

# SHIPPING LABELS CONTAIN

- State specification number with modifications, if applicable
- · Component designation
- · Type, if applicable
- · Manufacturer's name
- · Date of manufacture
- · Batch name
- · State lot number, if applicable
- · Directions for use
- · Warnings or precautions required by law

### **SHIPPING**

Freight Class 60

KEEP CONTAINER TIGHTLY CLOSED.
NOT FOR INTERNAL CONSUMPTION.
CONSULT MATERIAL SAFETY DATA SHEET
(MSDS) FOR MORE INFORMATION.
KEEP OUT OF REACH OF CHILDREN.
FOR INDUSTRIAL USE ONLY.

**Fyfe Co. LLC** 

Tyfo⊚ Fibrwrap⊚ Systems 8380 Miralani Drive, San Diego, CA 92126 Tel: 858.642.0694 Fax: 858.444.2982 E-mail: info@fyfeco.com www.fyfeco.com

Statement of Responsibility: The technical information and application advice in this publication is based on the present state of our best scientific and practical knowledge. As the nature of the information herein is general, no assumption can be made as to the product's suitability for a particular use or application, and no warranty as to its accuracy, reliability or completeness, either expressed or implied, is given other than those required by State legislation. The owner, his representative or the contractor is responsible for checking the suitability of products for their intended use. Field service, where provided, does not constitute supervisory responsibility. Suggestions made by the Fyfe Co., either verbally or in writing, may be followed, modified or rejected by the owner, engineer or contractor since they, and not the Fyfe Co., are responsible for carrying out procedure appropriate to a specific application.